



Concrete Coatings

OVERLAY-UNIVERSAL

WHITE OR GREY

Spray Bond Broom Texture

SINGLE COMPONENT CEMENTICIOUS OVERLAY

THE UNIVERSAL OVERLAY MIX IS A SINGLE-COMPONENT OVERLAY SYSTEM THAT BONDS TO ALL CLEAN CONCRETE SURFACES TO PRODUCE A ROCK HARD WEATHER PROOF SURFACE. COMES IN EITHER GREY OR WHITE 50 LB BAGS.

PRODUCT HIGHLIGHTS

- High bond, flexural and compressive strength. Consistent and evenly textured finish.
- Can be integrally colored with EZChem EZ Color Paks.
- Can be stained with EZChem Enviro Stain or Earthtone Stain for a wide array of decorative finishes.
- Can be sealed with EZChem Clear Acrylic Sealer or Colored Acrylic Sealer for a consistently colored and durable surface.
- **Packaged in 50lb bags**
- **Available in white and grey.**

USES

used for the finishing of concrete walls, stairs, pool decks, patios and walkways. It is easy to work with and enables the installation of a consistent and evenly textured finish.

Broom Finish Mix sets to a rock-hard surface that resists water penetration and provides a durable and beautiful textured surface.

Apply with a hopper gun to design and create a textured canvas.

QUICK LOOK:

Type :
Toxicity:
VOC's: Zero
Flammability: Non-flammable
Composition:
Odor: N/A
Coverage: Base coat = approx 175 Sq ft
Finish spray coat = approx 150 sq ft (100 to 200 sq.ft depending on texture)

**Coverage rates may vary depending on porosity, texture, application method and prior sealer application. Excess buildup should be avoided.*

Application Temperature: 50°-100°F
Cured: 28 days

FOR MORE INFORMATION,
PLEASE SEE SDS.





Concrete Coatings

SINGLE COMPONENT

OVERLAY-UNIVERSAL

SURFACE PREPARATION:

The surface must be clean and free of any dirt or debris and properly prepared according to the Technical Data Sheet for UNIVERSAL OVERLAY. Just before applying UNIVERSAL OVERLAY the substrate must be primed with Bond It primer. **Do not** allow Bond It primer to dry completely **MUST** be wet for use.

HOW TO USE:

UNIVERSAL OVERLAY is typically applied to a damp surface. Remove any puddles and standing water (Saturated surface dry) before installation. Add 50 lb bag of UNIVERSAL OVERLAY to approximately 5.5 quarts (minimum 4.5 maximum 6.5) of water. Mix in a clean 5-gallon pail with a ½" mixer drill (Do not use a cement mixer)

Add EZChem EZ COLOR PAK (blend the Color Pak into the water first) if integral color is desired.

Add half the powdered material to the water, mix until lump free, let sit for 5 minutes, then blend in the other half. Apply with a hopper gun, magic trowel (squeegee), steel pool trowel, brush, broom or roller

For a knockdown texture use 8-15 PSI through a relatively large orifice. As the wet, glossy material begins to dry to a matte or dull finish, it should be knocked down with a pool trowel or metal squeegee

For a bubble texture use 40 Psi through a relatively small orifice.

PRECAUTIONARY STATEMENT:

Obtain special instructions before use. Do not handle until all safety precautions have been read and understood. Avoid breathing dust/fume/gas/mist/vapours/spray. Wash hands thoroughly after handling. Do not eat, drink or smoke when using this product. Wear protective gloves/protective clothing/eye protection/face protection. Take off contaminated clothing and wash it before reuse. Store in a well-ventilated place. Keep container tightly closed. Store locked up. Dispose of contents/container to approved waste disposal site.

FIRST AID:

INHALATION: Move to fresh air to avoid nuisance symptoms.

SKIN CONTACT: Wash the affected area thoroughly with soap and water. Rinse well. If irritation develops Get Medical Help.

EYE CONTACT: Rinse thoroughly with water for 15 minutes, lifting both eyelids. If irritation persists, Get Medical Help.

INGESTION: Rinse mouth with water. Drink 2 glasses of water to dilute. Do not induce vomiting. Get Immediate Medical Help. Never give anything by mouth to an unconscious person.

IN CASE OF FIRE:

This product is not flammable.

TESTING DATA

Compressive Strength ASTM C-109	28 days 4000 PSI
Flexural Strength ASTM C-348	28 days 995
Tensile Strength ASTM C190	28 days 460 psi
Abrasion Resistance	28 day < 45%

FOR EMERGENCY HELP

24 Hours a Day contact:

INFOTRAC at 1-800-535-5053